

2399 Silver Wolf Drive • Henderson, NV 89011-4431 USA (702) 565-7500 • FAX (702) 565-3838 • FAX (800) 669-9811 www.armandmfg.com

## **Material Data Sheet**

## **Crystal Clear Static Dissipative Vinyl**

Gauge: 12 mil

Finish: Double Polish

Hand:

3S

Color: Clear

Width: Various

Tensile Strength: ASTM D-882

MD 2700 – 3300 PSI TD 2900 – 3500 PSI

Elongation: ASTM D-882

MD 250 – 350% TS 280 – 380%

100% Modulus ASTM D-882 MD 1600 – 2000 PSI TD 1400 – 1800 PSI

Surface Resistance:

10<sup>11</sup> Ohms per square

Measuring Device:

ATY-100 surface Resistance Meter

Test Method:

Employs parallel bar sensing methodology

Measurement Range;

 $10^3 - 10^{12}$ 

## Film Characteristics:

Formulated with anti static additive. Meets CSFM Fire Test Requirements Passes -10°F Cold Impact Testing

NOTE: This information is, to the best of the company's knowledge, accurate under numerous conditions: however, it does not apply in all cases. The summary chart is intended only as a guideline and all recommendations are made without guarantee since conditions of use are beyond our control.