INC

MATERIAL DATA

Poly and Vinyl Packaging and Specialty Products 2399 Silver Wolf Drive - Henderson, NV 89011-4431 USA (702) 565-7500 • FAX (702) 565-3838 • FAX (800) 669-9811 www.armandmfg.com • Email: sales@armandmfg.net

DURA-TUFF® 4798 ESD

Anti-microbial Conductive Coated Gurney/Mattress Fabric

Description: DURA-TUFF® 4798 ESD is a high-performance, flexible, vinyl covered fabric for use as Mattress Ticking, Gurney Mattress Covers, Drapery/Clean Room Curtains, Chair Underlays and other applications requiring a sewn or heat-sealed fabrication.

> Electrically, the product features a black conductive front and staticdissipative colored back. The unique multi-layer construction is engineered to able to be stitched, dimensionally stable, flame resistant, fluid proof, non-tacky, color stable, durable, mildew/fungal resistant, antibacterial and dirt/stain resistant.

Available Colors

#	Material Product ID	Color	Availability	
1	210 520 1407	Green / Black	Standard	
2	240 412 1102	Blue / Black	Upon request only	

Colors shown are approximations only. Actual color may vary and is not guaranteed.

TYPICAL PHYSICAL PROPERTIES							
Test and Methods	Imperial		Metric				
	Result	Unit	Result	Unit			
Weight FSTM191.5041	15 ± 1	oz/yd²	0.51 ± 0.03	kg/m²			
Thickness FSTM191.5030	0.02 ± 0.003	inches	0.51 ± 0.076	mm			
Adhesion (Face/Back) ASTM D751	4.6 / 7 ± 1.5	lbs/inch	20.5 / 31.1 ± 6.7	N/25mm			
Vertical Flammability (MD/CD) FSTM191.5903							
After Flame	5 / 4 ± 1	seconds	5 / 4 ± 1	seconds			
Char Length	5 / 5 ± 1	inches	127 / 127 ± 25.4	mm			
Hydrostatic Mullen FSTM191.5512	160 ± 10	PSI	1103.2 ± 68.9	kPa			
Tensile Strength-Grab (MD/CD) FSTM191.5100	116 / 130 ± 10	lbs	516 / 578 ± 44.5	Ν			
Tear Strength-Tongue (MD/CD) FSTM191.5134	6.3 / 8.8 ± 1.5	lbs	28.0 / 39.1 ± 6.7	Ν			
ESD/EOS							
Low Volts (Back)	7300 ohms						
10V (Face)	5.1 x 10 ⁹ ohms						
100V (Face)	4.0 x 10^4 ohms						
Standard Width	54	inches	1371.6	mm			

TYDTCAL DUVETCAL DRODEDTTEC

The values and information provided in this document have been provided directly to Armand from our material supplier. This information is given as an indication of typical values and provided without any obligation on our part.